

Matting agent

ACEMATT® HK 390

DESCRIPTION

ACEMATT® HK 390 is an untreated, very-fine-particle-sized matting agent based on precipitated silica. Due to its high compatibility, it can be used in a large variety of coatings. The improved orientation in coating systems effectively prevents mottling.

KEY BENEFITS

- high transparency
- super fine surface haptics
- universal usage in nearly all coating systems

EFFECT

Matting efficiency



Transparency



Viscosity



Smoothness/Haptic



Sedimentation behavior



SUITABILITY

waterborne	solventborne
●	●
●	●
●	●
●	●
●	●

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Car OEM coatings
- Plastic coatings
- Wood coatings
- General industrial coatings

TECHNICAL DATA

DOA absorption	330 ml/100g
Grindometer value	16 µm
particle size, d ₅₀	3.9 µm
pH value, 5% in water	6.6
specific surface area (N ₂)	255 m ² /g

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 1.5 - 7.0 %

PROCESSING INSTRUCTIONS

Addition to the coating as supplied or as a predilution is possible.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 24 months from the date of manufacture. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com