

AERODISP® W 7520 P

DESCRIPTION

AERODISP® W 7520 P is an aqueous dispersion of AEROSIL® fumed silica with a low viscosity and an alkaline pH value.

KEY BENEFITS


- low viscosity and easy-to-handle liquid
- water-based dispersion
- low rheological effect
- easy to incorporate

EFFECT

Anti-settling



Anti-sagging



Corrosion resistance



SUITABILITY

waterborne



solventborne



radiation-curing



1-pack coatings



2-pack coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Printing Inks
- General industrial coatings
- Paper coatings
- Decorative coatings

TECHNICAL DATA

appearance	white liquid
delivery form	dispersion
pH-value	9.0 - 10.0
SiO ₂ content	19-21 %
viscosity	max. 300 mPas

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 5 - 10 %

PROCESSING INSTRUCTIONS

Addition to the coating as supplied.

HANDLING & STORAGE

- When stored in an original unopened packaging, the product has a shelf life of 12 months from the date of manufacture.
- Keep away from freezing.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com