

DESCRIPTION

ALBIDUR® EP 2240 A shows the highest performance in enhancing impact resistance without influencing chemical or corrosion resistance properties of pigmented epoxy coatings.

KEY BENEFITS

- increased impact resistance
- increased tear resistance
- preservation of network density

SUITABILITY

waterborne	solventborne
●	●
100% system	
●	

**TYPICAL APPLICATIONS**

- General industrial coatings
- Marine coatings
- Protective coatings
- High solid industrial coatings

TECHNICAL DATA

active matter content	Approx. 40 wt-%
appearance	turbid
base resin	aromatic epoxy resin (DGEBA)
chemical description	dispersion of 40 wt-% Polydimethylsilicone spherical particles in DGEBA
epoxy equivalent weight (as supplied)	Approx. 300 g/eq
viscosity	35,000 mPas

SOLUBILITY

Water	Acetone
●	●
Methoxypropylacetate (MPA)	n-Butylacetate (nBA)
●	●
Methylisobutylketone (MIBK)	Xylene
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 10 - 20 wt-%

PROCESSING INSTRUCTIONS

Addition to the coating as supplied.

HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of 15 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com