

TEGO® Airex 940

DESCRIPTION

TEGO® Airex 940 shows good compatibility combined with effectiveness against both micro- and macro-foam. Ideally suited for high-solid and 2K solvent-free formulations.

KEY BENEFITS

- for solventborne and solvent-free coatings
- universal use in clear and pigmented formulations
- highly efficient with good compatibility

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating




Flooring




SUITABILITY


waterborne




solventborne



2-pack 100%



radiation-curing



pigmented coatings



clear coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Floor coatings
- General industrial coatings
- Protective coatings

TECHNICAL DATA

active matter content	approx. 15 %
appearance	clear liquid
chemical description	solution of a polymer with a tip of silicone
solvent	mineral spirit

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.2 - 1.5 %

PROCESSING INSTRUCTIONS

Suitable for addition during the let-down or even in clear formulations.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 24 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com