

TEGO® Airex 946

DESCRIPTION

TEGO® Airex 946 is a silicone-free deaerator that combines excellent deaeration with good compatibility. Ideally suited for solvent-free 2-pack epoxy formulations.

KEY BENEFITS

- for solvent-free coatings
- ideal for self-levelling epoxy floor coatings
- solvent-free, conforms to AgBB
- causes no oily surface after curing

APPLICATION RECOMMENDATION

Brush application/roller application



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne



solventborne



2-pack 100%



radiation-curing



pigmented coatings



clear coatings



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

Floor coatings

TECHNICAL DATA

active matter content	100 %
appearance	clear liquid
chemical description	formulation based on deaerating polymers, silicone-free

SOLUBILITY

Water



Ethanol



TPGDA



Acetone



Butylacetate



Mineral Spirits



● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.2 - 2.0 %

PROCESSING INSTRUCTIONS

- Addition as supplied is recommended.
- Easy to incorporate.

HANDLING & STORAGE

- When stored in an original unopened packaging between -40 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.
- When stored in an original unopened packaging, the product has a shelf life of 60 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com