

TEGO® Airex 960

DESCRIPTION

TEGO® Airex 960 is a deaerator for solventborne coating formulations.

KEY BENEFITS

- highly effective
- prevents patchy matting and surface irregularities in solventborne formulations through controlled orientation of the matting agent
- suitable for top coats

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
pigmented coatings	clear coatings
●	●

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Wood coatings
- General industrial coatings

TECHNICAL DATA

active matter content	approx. 25 %
appearance	clear liquid
chemical description	solution of an organo-modified polysiloxane
delivery form	liquid
solvent	xylene

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied on total formula weight: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

- Addition to the grind is recommended in pigmented formulations.
- Addition to the let-down or in clear coats requires high shear forces or predilution.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 48 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com