

CARBOWET® GA-211**DESCRIPTION**

CARBOWET® GA-211 is a non-ionic grind aid for waterborne formulations. Focus on pigment wetting. Additionally helps deaeration of the millbase.

KEY BENEFITS

- dynamic pigment and substrate wetting
- high deaeration activity
- minimal impact on coating properties

SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
direct grind	resin-containing pigment concentrates
●	●
resin-free pigment concentrates	
●	

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Architectural paints
- General industrial coatings
- Wood coatings
- Pigment concentrates

TECHNICAL DATA

active matter content	83 %
appearance	clear, pale yellow liquid
chemical description	surface active polymers
solvent	water
viscosity at 21°C	Approx. 90 mPas

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 1.0 - 3.0 %

PROCESSING INSTRUCTIONS

Add before grinding.

HANDLING & STORAGE

- When stored in an original unopened packaging, the product has a shelf life of 24 months from the date of manufacture.
- Keep away from direct sunlight. Keep containers tightly closed in a dry, cool and well-ventilated place. Product is freeze-thaw stable; if it phase separates or freezes at colder temperatures, warm container to 40°C and mix thoroughly before use.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com