## **TEGO® Dispers 645**

### **DESCRIPTION**

TEGO® Dispers 645 is a polymeric wetting and dispersing additive for solventborne formulations with a medium to high polarity. Provides good viscosity reduction for all kinds of pigments and a very high color strength especially with organic pigments and pigment blacks.

#### **KEY BENEFITS**

- very good for organic pigments and carbon blacks
- very good viscosity reduction
- broad compatibility

EFFECT
Viscosity reduction with organic pigments/carbon blacks
Color intensity/gloss with organic pigments/carbon blacks
Viscosity reduction with inorganic pigments/fillers
Color intensity/gloss with inorganic pigments/fillers

waterborne	solventborne
•	•
2-pack 100%	radiation-curing
•	•
direct grind	resin-containing pigment concentrates
0	•

### **TYPICAL APPLICATIONS**

- Pigment concentrates
- Wood coatings
- General industrial coatings

# active matter content 100 % appearance clear liquid

high molecular weight polymer

Water	Ethanol
•	•
TPGDA	Butylacetate
•	•
Mineral Spirits	
•	

### RECOMMENDED ADDITION LEVEL

chemical description

As supplied calculated on inorganic pigment: 1.0 - 15.0 % As supplied calculated on organic pigment: 5.0 - 25.0 % As supplied calculated on carbon black: 10.0 - 40.0 % Recommended addition level for co-grind: 0.5 - 3.0 %

### **PROCESSING INSTRUCTIONS**

Add to the grind before dispersion.

### HANDLING & STORAGE

- When stored in an original unopened packaging, the product has a shelf life of 24 months from the date of manufacture.
- At low temperatures, reversible turbidity can occur.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | <a href="https://www.coating-additives.com">www.coating-additives.com</a>

