

TEGO® Dispers 671

DESCRIPTION


TEGO® Dispers 671 is a polymeric wetting and dispersing additive for solventborne formulations. Provides high color strength, especially with organic pigments. Dispersions of carbon black pigments show a low viscosity and a blueish undertone.

KEY BENEFITS

- high color strength with organic pigments
- blueish undertone with carbon black pigments

EFFECT

Viscosity reduction with organic pigments/carbon blacks



Color intensity/gloss with organic pigments/carbon blacks



Viscosity reduction with inorganic pigments/fillers



Color intensity/gloss with inorganic pigments/fillers



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
direct grind	resin-containing pigment concentrates
●	●
resin-free pigment concentrates	universal pastes
●	●
● not suitable ● partly suitable ● suitable	

TYPICAL APPLICATIONS

- Pigment concentrates
- Car repair coatings
- General industrial coatings

TECHNICAL DATA

active matter content	approx. 40 %
amine value (as supplied)	Approx. 10 mg KOH/g
appearance	clear to slightly hazy liquid (product properties are not affected by haziness)
chemical description	solution of a high molecular weight polymer
solvent	xylene / butyl acetate / methoxypropylacetate 3 : 1 : 1
viscosity at 25 °C	Approx. 800 mPas

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Butylacetate
●	●
Mineral Spirits	
●	
● not soluble ● partly soluble ● suitable	

RECOMMENDED ADDITION LEVEL

As supplied calculated on inorganic pigment: 5.0 - 40.0 %
 As supplied calculated on organic pigment: 15.0 - 40.0 %
 As supplied calculated on carbon black: 40.0 - 85.0 %
 Recommended addition level for co-grind: 0.5 - 3.0 %

PROCESSING INSTRUCTIONS

Add to the grind before dispersion.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 48 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com