


**DESCRIPTION**

TEGO® Flow ATF 2 shows highly effective anti-crater properties for solventborne coatings. It ensures wetting even on insufficiently cleaned or contaminated substrates.

**KEY BENEFITS**

- excellent anti-crater effect
- highly efficient

**EFFECT****Anti-crater effect****Flow promotion****Slip effect****Anti-blocking****Low foam****TECHNICAL DATA**

<b>active matter content</b>	100 %
<b>appearance</b>	clear liquid
<b>chemical description</b>	formulation of special dimethyl polysiloxanes

**SOLUBILITY**

<b>Water</b>	<b>Ethanol</b>
●	●
<b>TPGDA</b>	<b>Acetone</b>
●	●
<b>Butylacetate</b>	<b>Mineral Spirits</b>
●	●

● not soluble ● partly soluble ● soluble

**SUITABILITY**

<b>waterborne</b>	<b>solventborne</b>
●	●
<b>2-pack 100%</b>	<b>radiation-curing</b>
●	●
<b>pigmented coatings</b>	<b>clear coatings</b>
●	●

● not suitable ● partly suitable ● suitable

**RECOMMENDED ADDITION LEVEL**

As supplied calculated on total formulation: 0.1 - 0.5 %

**PROCESSING INSTRUCTIONS**

- Addition to the coating as supplied or as a predilution is possible.
- Predilution in a suitable solvent simplifies dosage and incorporation.

**HANDLING & STORAGE**

When stored in an original unopened packaging, the product has a shelf life of 48 months from the date of manufacture.

**TYPICAL APPLICATIONS**

- Architectural paints
- General industrial coatings
- Floor coatings
- Screen Inks

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)