

# TEGO® Foamex 11

## DESCRIPTION

TEGO® Foamex 11 is a highly efficient, especially low-VOC defoamer emulsion based on polyether siloxane technology. Developed for architectural paints.

## KEY BENEFITS

- alternative to mineral oil defoamers
- suitable for ecolabel-compliant and low-VOC formulations
- suitable for medium- to high-PVC formulations

## APPLICATION RECOMMENDATION

### Brush application/roller application



### Airless spraying



### Compressed air spraying



### Flexo/gravure printing



### Dip coating, flow coating, curtain coating



### Flooring



## SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●
● not suitable   ● partly suitable   ● suitable	

## TYPICAL APPLICATIONS

Architectural Paints

## TECHNICAL DATA

active matter content	15 %
appearance	white thixotropic liquid
chemical description	emulsion of a polyether siloxane copolymer, silica-free
solvent	solvent-free

## SOLUBILITY

For stability reasons emulsions may not be diluted by organic solvents.

## RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

## PROCESSING INSTRUCTIONS

- Before use, mix briefly with low shear forces.
- Addition to the coating as supplied.
- Addition may be either in the grind or during the let-down procedure.

## HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40°C, the product has a shelf life of 24 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)