

TEGO® Foamex 855

DESCRIPTION

TEGO® Foamex 855 is a very effective defoamer emulsion based on polyether siloxane technology. Suitable for mid- to high-PVC formulations.

KEY BENEFITS

- good long-term effectiveness
- suitable for high-viscosity formulations
- recommended for addition during the let-down stage

APPLICATION RECOMMENDATION

Brush application/roller application



Airless spraying



Compressed air spraying



Flexo/gravure printing



Dip coating, flow coating, curtain coating



Flooring



SUITABILITY

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
addition to the grinding stage	addition to the let-down stage
●	●
● not suitable ● partly suitable ● suitable	

TYPICAL APPLICATIONS

- Architectural paints
- General industrial coatings

TECHNICAL DATA

active matter content	20 %
appearance	white thixotropic liquid
chemical description	emulsion of a polyether siloxane copolymer, contains fumed silica
solvent	solvent-free

SOLUBILITY

For stability reasons emulsions may not be diluted by organic solvents.

RECOMMENDED ADDITION LEVEL

As supplied calculated on carbon black: 0.1 - 1.0 %

PROCESSING INSTRUCTIONS

- Before use, mix briefly with low shear forces.
- Addition to the coating as supplied.
- Long term effectiveness of the product is dependent on the formulation and should be tested in individual formulations.

HANDLING & STORAGE

- When stored in an original unopened packaging between +4 and +40°C, the product has a shelf life of 24 months from the date of manufacture.
- Keep away from freezing.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com