TEGO® Glide 130

DESCRIPTION

TEGO® Glide 130 shows a very good anti-crater effect in solventborne coatings.

KEY BENEFITS

- excellent anti-crater effect
- excellent leveling
- highly efficient

EFFECT	
Anti-crater effect	
Flow promotion	
Slip effect	
Anti-blocking	
Low foam	

/aterborne	solventborne
5	•
2-pack 100%	radiation-curing
	•
pigmented coatings	clear coatings
	•

TYPICAL APPLICATIONS

- Wood coatings
- Architectural paints
- General industrial coatings
- Printing Inks

TECHNICAL DATA	
active matter content	100 %
appearance	clear liquid
chemical description	polyether siloxane copolymer

Vater	Ethanol
	•
PGDA	Acetone
	•
utylacetate	Mineral Spirits
	•

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 0.5 %

PROCESSING INSTRUCTIONS

- Addition to the coating as supplied or as a predilution is possible.
- Predilution in a suitable solvent simplifies dosage and incorporation.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 60 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried on only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com

