

Slip and flow additive

# TEGO® Glide 415

## DESCRIPTION

TEGO® Glide 415 shows excellent flow and leveling properties and displays a strong slip effect, especially in solventborne coatings. It is recoatable and highly compatible.

## KEY BENEFITS

- excellent leveling
- highly compatible
- recoatable

## EFFECT

### Anti-crater effect



### Flow promotion



### Slip effect



### Anti-blocking



### Low foam



## SUITABILITY

### waterborne



### solventborne



### 2-pack 100%



### radiation-curing



### pigmented coatings



### clear coatings



● not suitable ● partly suitable ● suitable

## TECHNICAL DATA

**active matter content** 15 %

**appearance** clear liquid

**chemical description** solution of a polyether siloxane copolymer

**solvent** phenoxyethanol / xylene 1 : 4

## SOLUBILITY

### Water



### Ethanol



### TPGDA



### Acetone



### Butylacetate



### Mineral Spirits



● not soluble ● partly soluble ● suitable

## RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.1 - 1.0 %

## PROCESSING INSTRUCTIONS

- Addition as supplied is recommended.
- Easy to incorporate.

## HANDLING & STORAGE

When stored in an original unopened packaging between -40 and +40 °C, the product has a shelf life of at least 36 months from the date of manufacture.

## TYPICAL APPLICATIONS

- Car OEM coatings
- Car repair coatings
- Plastic coatings
- Wood coatings

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)