

Slip and flow additive

# TEGO® Glide 466

## DESCRIPTION

TEGO® Glide 466 shows an excellent anti-crater effect on contaminated substrates. It is very effective and can be used in a broad range of different coatings.

## KEY BENEFITS

- excellent anti-crater effect
- good slip effect
- highly efficient

## EFFECT

### Anti-crater effect



### Flow promotion



### Slip effect



### Anti-blocking



### Low foam



## SUITABILITY

### waterborne



### solventborne



### 2-pack 100%



### radiation-curing



### pigmented coatings



### clear coatings



● not suitable ● partly suitable ● suitable

## TYPICAL APPLICATIONS

- General industrial coatings
- Floor coatings
- Screen Inks
- Architectural paints

## TECHNICAL DATA

active matter content	100 %
appearance	clear liquid
chemical description	dimethyl polysiloxane

## SOLUBILITY

Water	Ethanol
●	●
TPGDA	Acetone
●	●
Butylacetate	Mineral Spirits
●	●

● not soluble ● partly soluble ● soluble

## RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.05 - 0.5 %

## PROCESSING INSTRUCTIONS

- Addition to the coating as supplied or as a predilution is possible.
- Predilution in a suitable solvent simplifies dosage and incorporation.

## HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40°C, the product has a shelf life of at least 36 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | [www.coating-additives.com](http://www.coating-additives.com)