

TEGO® Hammer 300.000

DESCRIPTION

TEGO® Hammer 300.000 provides a hammer-tone finish effect by controlling incompatibility within the coating formulation.

KEY BENEFITS

provides a hammer-tone finish effect to paints and coatings

SUITABILITY

| waterborne | solventborne |
|---------------------------------------------|--------------|
| ● | ● |
| radiation-curing | 100% system |
| ● | ● |
| ● not suitable ● partly suitable ● suitable | |

TYPICAL APPLICATIONS

General industrial coatings

TECHNICAL DATA

| | |
|-----------------------|------------------------|
| active matter content | 100 % |
| appearance | clear colorless liquid |
| chemical description | polydimethylsiloxane |

SOLUBILITY

| Mineral Spirits | TPGDA |
|------------------------------------------|---------|
| ● | ● |
| Water | Acetone |
| ● | ● |
| Butylacetate | Xylene |
| ● | ● |
| Butyl glycol | Styrene |
| ● | ● |
| ● not soluble ● partly soluble ● soluble | |

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 0.01 - 0.5 %

PROCESSING INSTRUCTIONS

- Addition at the let-down stage is recommended.
- Appearance of the resulting hammer finish also depends on suitable pigmentation of the coating.

HANDLING & STORAGE

When stored in an original unopened packaging, the product has a shelf life of 60 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com