

DESCRIPTION

LA-D 1621 is a polymeric wetting and dispersing additive used to disperse pigments with non-polar long-oil alkyd resins. Its outstanding viscosity reduction can be observed especially in low-polar solvents. Especially suitable for organic pigments.

KEY BENEFITS

- highly suitable for non-polar long oil alkyd resin system
- excellent viscosity reduction for carbon black, organic, and inorganic pigments

EFFECT**Viscosity reduction with organic pigments/carbon blacks****Color intensity/gloss with organic pigments/carbon blacks****Viscosity reduction with inorganic pigments/fillers****Color intensity/gloss with inorganic pigments/fillers****SUITABILITY**

waterborne	solventborne
●	●
2-pack 100%	radiation-curing
●	●
high solids	direct grind
●	●
resin-containing pigment concentrates	resin-free pigment concentrates
●	●
universal pastes	
●	

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Inkjet Inks
- Pigment concentrates
- Architectural paints

TECHNICAL DATA

active matter content	40 %
amine value (as supplied)	Approx. 30 mg KOH/g
appearance	liquid
chemical description	solution of a high molecular weight polymer
solvent	Methoxypropylacetate / Butyl Acetate 1:1
viscosity at 25 °C	Approx. 200 mPas

SOLUBILITY

Water	Ethanol
●	●
TPGDA	Butylacetate
●	●
Mineral Spirits	
●	

● not soluble ● partly soluble ● soluble

RECOMMENDED ADDITION LEVEL

As supplied calculated on inorganic pigment: 5.0 - 15.0 %
 As supplied calculated on organic pigment: 30.0 - 80.0 %
 As supplied calculated on carbon black: 50.0 - 100.0 %

PROCESSING INSTRUCTIONS

Add to the grind before dispersion.

HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 24 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com