

DESCRIPTION

TEGO® Phobe 6600 is a formulation of a polysiloxane resin / silane-blend for waterborne impregnations and primers.

KEY BENEFITS

- applicable on neutral to slightly alkaline substrates
- provides deep substrate penetration
- provides a good water beading effect

EFFECT**Reduced water uptake****Water beading effect****Low tendency to pick up dirt****Early water resistance****SUITABILITY****waterborne****solventborne****2-pack 100%****radiation-curing****powder**

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Architectural paints
- Wood coatings

TECHNICAL DATA

active matter content	approx. 50 %
appearance	white liquid
chemical description	emulsion of a polysiloxane resin/silane-blend
solvent	solvent-free

SOLUBILITY

For stability reasons emulsions may not be diluted by organic solvents.

RECOMMENDED ADDITION LEVEL

As supplied calculated on total formulation: 5.0 - 25.0 %

PROCESSING INSTRUCTIONS

- Dilutions ready for sale should be protected with a preservative.
- For hydrophobic primers, a combination with acrylic hydrosols is recommended. The higher the absorption of the substrate, the higher the hydrosol content should be.
- For hydrophobic impregnations, the active matter content should be diluted to 5-25%.

HANDLING & STORAGE

When stored in an original unopened packaging between +4 and +40 °C, the product has a shelf life of at least 18 months from the date of manufacture.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com