

DESCRIPTION

Silicone Epoxy Hybrid Resin

KEY BENEFITS

- excellent adhesion, chemical and solvent resistance
- excellent corrosion resistance
- very good thermal shock resistance

SUITABILITY

waterborne	solventborne
●	●
● not suitable	● partly suitable
	● suitable

● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Protective coatings
- Heatstable Coatings
- exhaust systems, mufflers

TECHNICAL DATA

appearance	clear to hazy colored liquid (product properties are not affected by haziness)
non-volatile content	Approx. 52 %
solvent	methoxypropylacetate
viscosity at 25 °C	Approx. 1,000 mPas

SOLUBILITY

Water	Butylacetate
●	●
Methylisobutylketone (MIBK)	Xylene
●	●
Dowanol MPA	Cyclohexanone
●	●
Butanol	
●	
● not soluble ● partly soluble ● soluble	

PROCESSING INSTRUCTIONS

- Because of the strong yellowing, only the formulation of dark colors is recommended.
- Use with metallic pigments and special formulations to obtain continuous heat-resistance of up to 450 °C.
- In combination with alcoxy-functional resins, we do not recommend the use of alcohols or hydroxy-functional glycol ethers as solvents.
- Application by spray (incl. electrostatic) and dipping.

CURING CONDITIONS

250 °C / 30 min.

HANDLING & STORAGE

- When stored in an original unopened packaging, the product has a shelf life of 24 months from the date of manufacture.
- Contact with tin (e.g. with metal containers) will shorten the storage stability. Keep dry. Contact with moisture causes gelation.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com