

Specialty filler

TEGO® Therm HPG 4000

DESCRIPTION

TEGO® Therm HPG 4000 is a purely mineral product based on silicone dioxide. TEGO® Therm HPG 4000 can be combined with other materials to produce thermal insulation coatings.

KEY BENEFITS

- superinsulation properties
- outstanding low thermal conductivity at high temperature range
- high hydrophobicity
- excellent heat & mechanical stability
- non-combustible

EFFECT

Brightness



Absorptive capacity



Gloss reduction



Smooth Surface Profile



SUITABILITY

waterborne



● not suitable ● partly suitable ● suitable

TYPICAL APPLICATIONS

- Insulation coatings
- Ovens, furnaces, pipelines, incinerators
- Heat-stable coatings for industrial facilities
- Architectural paints

TECHNICAL DATA

carbon content	< 2.5 (without opacifier) %
delivery form	free-flowing powder
loss on drying	< 0.5 %
particle size, d ₅₀	Approx 300 µm
particle size, d ₉₅	< 1000 µm
pH-value	6.5 - 8.5
specific surface area (BET)	Approx 115 m ² /g
tamped density	Approx. 225 g/l
thermal conductivity at 10°C	Approx. 0.024 W/m/K

PROCESSING INSTRUCTIONS

- Incorporate the product under low shear forces with moderate to high agitation.
- Homogenize the content of the package carefully directly before use.

HANDLING & STORAGE

The product is supplied in 200 L metal drums with 30 kg content. We recommend storing the product under dry conditions (e.g., closed warehouse). The product should be used within 5 years after production.

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Evonik Operations GmbH | Goldschmidtstraße 100, 45127 Essen, Germany | Telefon +49 201 173-2222 Telefax +49 201 173-1939 | www.coating-additives.com