

## Product information

# ANCAMIDE<sup>®</sup> 2426

## Curing Agent

### DESCRIPTION

Ancamide 2426 curing agent is a modified, low-viscosity, blush-resistant amidoamine curing agent for use in coatings, civil engineering and adhesive applications.

### TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Light Brown Liquid		
Colour	8	Gardner	ASTM D 1544-80
Viscosity @ 77°F	650	cP	ASTM D-445-83, Brookfield, RVTD, Spindle 4
Specific Gravity @ 77°F	0.952		ASTM D 1475-85
Amine Value	380	mg KOH/g	Perchloric Acid Titration
Flash Point	> 400	°F	Seta Flash Closed Cup
Equivalent Wt/{H}	93		
Recommended use Level	49	phr	EEW=190

### ADVANTAGES

- Free of benzyl alcohol and other plasticizers and solvents
- Excellent blush resistance
- Long pot life
- Low viscosity
- Excellent hardness development
- Good resistance to immersion in many aqueous solutions
- Compliant with FDA regulation 21 CFR 175.300 forcoatings for containers having a capacity of 1000 gallons or more when such containers are intended for repeated use in contact with alcoholic beverages containing up to 8 percent alcohol by volume

### APPLICATIONS

- Brewery tank linings
- High and 100% solids coatings
- Potable water applications

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 2426 curing agent.

## TYPICAL CURE SCHEDULE

**7 days at ambient temperature.**

## PERFORMANCE DATA

**A 15 minute induction time is recommended for optimum film formation without amine exudate.**

## TYPICAL HANDLING PROPERTIES \*

Property	Value	Unit	Method
Mixed Viscosity @ 77°F	3,400	cP	
Gel Time (150g mix @ 77°F)	245	min	Techne GT-3 Gelation Timer
Thin Film Set Time @ 77°F	14	h	BK Drying Recorder
Peak Exotherm (150g mix @ 77°F)	95	°F	ASTM D 2471-71
Peak Exotherm Time	200	min	ASTM D 2471-71

## TYPICAL PERFORMANCE \*

Property	Value	Unit	Method
Glass Transition Temp	118	°F	ASTM D 3418-82

\*Ancamide 2426 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

## SUPPLEMENTARY DATA

**PLASTICIZER-FREE:** Ancamide 2426 curing agent contains no plasticizers or solvents, enabling the formulator the capability to formulate coatings and linings which have extremely low levels of extractables. Formulations can be developed at very high solids and 100% solids, with excellent pot life.

**BLUSH RESISTANCE:** Ancamide 2426 curing agent offers significantly improved blush resistance compared with standard amidoamine curing agents. At ambient temperature, Ancamide 2426 curing agent-based films have only a slight haze with no induction time, and no haze with 15 minutes of induction time.

**HARDNESS DEVELOPMENT:** Pendulum hardness with no induction time was measured for 3-mil DFT clear films based on Ancamide 2426 curing agent. Excellent hardness was achieved within the typical 7-day cure schedule, and the rate of hardness build accelerated within the first 3 days.

Property	1 day	3 days	7 days	14 days
Hardness	5	56	92	110

**CORROSION RESISTANCE:** 4-mil thick clearcoat films on grit blasted steel panels and 5-mil clear films on cold rolled steel were tested for 1000 hours for humidity resistance per ASTM D-2247. The schedule utilized was 10 hours wet at 104°F followed by 2 hours dry at 113°F. There was no blistering or visible corrosion at the end of the test period on either substrate.

**CHEMICAL RESISTANCE:** Ancamide 2426 curing agent offers good chemical resistance to many aqueous solutions in immersion conditions. Results for liquid epoxy resin (EEW = 190) cured for 7 days at ambient temperature are shown below. Chemical resistance data is expressed as percent weight change. Testing was completed in accordance with ASTM D543-83.

### IMMERSION TIME (DAYS)

Property	1	3	7	28	60
Deionized Water	0.4	0.6	0.8	1.7	2.4
10% Acetic Acid	4.9	7.9	11.2	18.8	22.9
Ethanol	6.3	9.3	12.9	25.0	25.0
Xylene	24.4	D	D	D	D
1,1,1, Trichloroethane	33.5	35.5	D	D	D
50% Sodium Hydroxide	0.0	0.0	0.1	0.2	0.3
70% Sulfuric Acid	0.3	0.6	1.0	3.6	5.7

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

**Disclaimer**

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**EVONIK OPERATIONS GMBH**

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**EVONIK CORPORATION**

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

**EVONIK SPECIALTY CHEMICALS  
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

