

Product information

ANCAMIDE[®] 2711

Curing Agent

DESCRIPTION

Ancamide 2711 curing agent is a formulated amidoamine intended for use with liquid epoxy resins. It has fast cure speed and better compatibility with resin compared with standard amidoamines.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Clear Amber liquid		
Color	≤ 9	Gardner	ASTM D1544-80
Viscosity @ 25°C	100-300	cP	ASTM D2196-05, Brookfield RVTD
Amine Value	540-600	mg KOH/g	Perchloric acid titration
Specific Gravity @ 21°C	0.96		
Equivalent Wt/{H}	75		
Recommended Use Level	40	PHR	Bisphenol A diglycidyl ether resin (EEW=190)
Gel Time @ 25°C (150 g)	78	min	Techne GT-3 Gelation Timer

ADVANTAGES

- Excellent adhesion to concrete
- Fast cure

APPLICATIONS

- Concrete primers, adhesives and bonding agents
- Mortars and grouts

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamide 2711 curing Agent.

TYPICAL CURE SCHEDULE

7 days at ambient temperature

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

