

Product information

ANCAMIDE[®] 501

Curing Agent

DESCRIPTION

Ancamide 501 curing agent is an accelerated amidoamine for use in curing liquid epoxy resins. It offers faster cure speed and improved chemical resistance over unmodified amidoamines.

TYPICAL PROPERTIES

Property	Value	Unit
Appearance	Amber Liquid	
Color	7	Gardner
Viscosity @ 77°F	600	cP
Amine Value	550	mg KOH/g
Specific Gravity @ 77°F	0.980	
Density @ 77°F	8.2	lb/gal
Flash Point (closed cup)	259	°F
Equivalent Wt{H}	68	
Recommended Use Level	35	phr, EEW=190

BENEFITS

- Faster cure than standard amidoamines
- Low viscosity
- Excellent bonding for construction materials, particularly concrete

APPLICATIONS

- Trowelable flooring
- Concrete coatings and primers
- Repair mortars and patching compounds
- Concrete adhesives and grouts

STORAGE AND HANDLING

Refer to the Safety Data Sheet on Ancamide 501 curing agent.

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

TYPICAL CURE SCHEDULE

- 2 to 7 days at ambient temperature.
- 2 h at 140°F plus 1 h at 212°F.

TYPICAL HANDLING PROPERTIES*

Property	Value	Unit
Mixed Viscosity @ 77°F	3,000	cP
Gel Time (150g mix @ 77 °F)	40	min
Thin Film Set Time @ 77 °F	7.5	h
Peak Exotherm (100g mix @ 77°F)	316	°F
Peak Exotherm Time	55	min

TYPICAL PERFORMANCE (WITH BIS-A RESIN—A*)

Property	Value	Unit
7 day cure @ 77°F		
Heat Deflection Temperature (ASTM D648-264 psi)	116	°F
Barcol Hardness (Model GYZJ-935)	79	
Bond Strength (mild steel to mild steel)	2,020	psi
Tensile Strength	6,180	psi
Tensile Modulus	457	thousand psi

TYPICAL PERFORMANCE (WITH DILUTED RESIN—B*)

Property	Value	Unit
7 day cure @ 77°F		
Compressive Strength and Yield	13,200	psi
Compressive Modulus	318	thousand psi
Tensile Strength	7,800	psi
Tensile Modulus	352	thousand psi
Tensile Elongation at Break	7.9	%
Flexural Strength	14,000	psi
Flexural Modulus	396	thousand psi

(A*) Ancamide 501 curing agent formulated with standard Bisphenol-A (DGEBA, EEW=190) epoxy resin.

(B*) Ancamide 501 curing agent with 90% DGEBA resin (EEW=190) and 10% Epodil® 748 diluent (C₁₂-C₁₄ alkyl glycidyl ether).

Ancamide® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chungong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

