

**ANCAMINE<sup>®</sup> 1856****Curing Agent****DESCRIPTION**

Ancamine 1856 curing agent is a modified aliphatic amine with high reactivity. Typical of Mannich-Base curing agents, Ancamine 1856 curing agent has the ability to cure well under adverse conditions of high humidity and low temperatures (down to 30°F). Ancamine 1856 is most commonly used as an accelerator for other curing agents.

**TYPICAL PROPERTIES**

Property	Value	Unit
Appearance	Yellow Liquid	
Colour	5	Gardner
Viscosity @ 77°F	3,000	cP
Amine Value	460	mg KOH/g
Specific Gravity @ 77°F	1.12	
Flash Point (closed cup)	230	°F
Equivalent Wt/{H}	73	
Recommended Use Level	40	phr, EEW=190

**BENEFITS**

- Fast cure and rapid development of hardness
- High strength and modulus
- Excellent cure at low temperatures
- Reduced tendency to form carbamates with carbon dioxide in the atmosphere during cure
- Very good chemical resistance to distilled water, inorganic acids and alkalis; good against organic acids and alkalis and many organic solvents

## APPLICATIONS

- Concrete repair mortars
- Solvent-free and high-solids coatings
- Adhesives
- Tank linings and chemically resistant coatings
- Accelerator for other curing agents

When used in conjunction with a diluent (e.g., Epodil® LV5 diluent, benzyl alcohol), Ancamine 1856 curing agent is suitable for use in civil engineering applications where its low temperature cure characteristics and ability to cure in damp conditions are an advantage.

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## STORAGE AND HANDLING

Refer to the Safety Data Sheet on Ancamine 1856 curing agent.

## TYPICAL CURE SCHEDULE

**2-7 days at ambient temperature.**

## TYPICAL HANDLING PROPERTIES\*

Property	Value	Unit
Gel Time (150g mix @ 77°F )	9	min
Thin Film Set Time		
@ 77°F	1.8	h
@ 40°F	3.5	h
Peak Exotherm (100g mass)	289	°F
Peak Exotherm Time	18	min

\*Ancamine 1856 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.



## TYPICAL PERFORMANCE PROPERTIES\*

Property	Value	Unit
<b>(Cured 7 days @ 77°F)</b>		
<b>Compressive Strength</b>	15,400	psi
<b>Compressive Modulus</b>	402	thousand psi
<b>Tensile Strength</b>	12,400	psi
<b>Tensile Modulus</b>	606	thousand psi
<b>Elongation</b>	4.4	%
<b>Flexural Strength</b>	20,900	psi
<b>Flexural Modulus</b>	658	thousand psi
<b>Heat Deflection Temperature (ASTM D648-264 psi)</b>	132	°F
<b>Barcol Hardness (Model GYZJ-935)</b>	86	
<b>Bond Strength (mild steel to mild steel)</b>	1,957	psi

\*Ancamine 1856 curing agent formulated with standard Bisphenol-A based (DGEBA, EEW=190) epoxy resin.

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

### Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

### EVONIK OPERATIONS GMBH

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

### EVONIK CORPORATION

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

### EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers  
55, Chungong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

