

Product information

ANCAMINE[®] 2410B75

Curing Agent

DESCRIPTION

Ancamine 2410B75 curing agent is a 75% solids, highly monodispersed adduct of a polyamine and liquid epoxy resin cut in butanol and is designed for use in coatings and related applications.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Light yellow liquid		
Color	2	Gardner	ASTM D 1544-80
Viscosity @ 77°F (25°C)	11,000	cP	Brookfield RVTD, spindle 4
Amine Value	340	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 70°F (21°C)	1.05		
Equivalent Wt/{H}	114		
Recommended Use Level	60	PHR	With Bisphenol-A diglycidyl ether (EEW=190)

ADVANTAGES

- Excellent resistance to a wide variety of aggressive chemicals
- Fast dry speed combined with a long pot life
- Low residual polyamine for reduced amine blush
- Excellent dilution profile (as a result of narrow molecular weight distribution) for easier handling and reduced VOC
- Can be used in food contact applications

APPLICATIONS

- Tank linings
- Chemically resistant high solids coatings
- Coatings for food contact
- As an accelerator for other curing agents where improved chemical resistance and dry speed are required

STORAGE LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature.

STORAGE AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2410B75 curing agent.

TYPICAL HANDLING PROPERTIES

Property	Value	Unit	Method
Thin Film Set Time 77°F (25°C)	2	h	BK Drying Recorder Phase
Typical cure schedule	2- 7	days	

TYPICAL PERFORMANCE PROPERTIES

See supplementary information

ANCAMINE® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

