

## Product information

# ANCAMINE<sup>®</sup> 2719

## Curing Agent

### DESCRIPTION

Ancamine 2719 curing agent is a nonyl- and p-tert-butyl phenol free aliphatic polyamine Mannich base curing agent designed for use with liquid epoxy resin. It is of low viscosity and highly reactive at low temperatures ~5°C. Ancamine 2719 will react with liquid epoxy resins at low temperature to produce a highly chemical resistant surface coating.

### TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Brown liquid		
Colour	14	Gardner	ASTM D 1544-80
Viscosity @ 25°C	300-500	mPa.s	Brookfield RVTD, Spindle 4
Amine Value	340-380	mg KOH/g	Perchloric Acid Titration
Specific Gravity @ 21°C	1.03		
Equivalent	75	Wt/{H}	
Recommended use Level	40	PHR	With Bisphenol A diglycidyl ether (EEW=190)

### ADVANTAGES

- Fast cure
- Low temperature cure
- Excellent chemical resistance
- Nonyl phenol free

### APPLICATIONS

- Protective coatings
- Industrial applications
- Potable water coatings

## SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

## PACKAGING AND HANDLING

Refer to the Safety Data Sheet for Ancamine 2719 curing agent.

## TYPICAL HANDLING PROPERTIES\*

Property	Value	Unit	Method
Mix Viscosity 25°C	2400	mPa.s	
Gel Time (150g mix at 25°C)	20	min	Techne GT-3 Gelation Timer
Thin Film Set Time 23°C	2.5	h	BK Drying Recorder Phase III
Hardness Shore D at 25°C (24h)	80		DIN 53505
Hardness Shore D at 10°C (24h)	72		DIN 53505
Typical cure schedule	2-7	days	

## TYPICAL PERFORMANCE PROPERTIES\*

Property	Value	Unit	Method
Tensile Strength	52	MPa	ISO 527
Tensile Modulus	3.1	GPa	ISO 527
Tensile Elongation at Break	4.9	%	
Flexural Strength	106	MPa	ISO 178
Flexural Modulus	2830	MPa	ISO 178
Compressive Strength	108	MPa	ASTM C579-96
Compressive Modulus	1865	MPa	ASTM C579-96

\*With Bisphenol A diglycidyl ether (EEW=190)

Ancamine® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

**Disclaimer**

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**EVONIK OPERATIONS GMBH**

Business Line Crosslinkers  
Paul-Baumann-Str. 1  
45764 Marl  
Germany

[www.evonik.com/crosslinkers](http://www.evonik.com/crosslinkers)

**Product Information:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**Sample Request:** [APCSE@evonik.com](mailto:APCSE@evonik.com)

**EVONIK CORPORATION**

Business Line Crosslinkers  
7001 Hamilton Boulevard  
Trexlerstown, PA 18087  
USA

[CrosslinkersProinfo@evonik.com](mailto:CrosslinkersProinfo@evonik.com)

[Crosslinkers-Samples@evonik.com](mailto:Crosslinkers-Samples@evonik.com)

**EVONIK SPECIALTY CHEMICALS  
(SHANGHAI) CO., LTD.**

Business Line Crosslinkers  
55, Chundong Road  
Xinzhuang Industry Park  
Shanghai, 201108  
China

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

[CL-Asiainfo@evonik.com](mailto:CL-Asiainfo@evonik.com)

