

Product information

ANCAMINE[®] 2844

Curing Agent

DESCRIPTION

Ancamine[®] 2844 curing agent is a low viscosity high solids amine curing agent designed for use in plural component spray applications. It exhibits ultra-fast cure and rapid property development at low temperature providing excellent surface appearance.

TYPICAL PROPERTIES

Property	Value	Unit	Method
Appearance	Colorless to light yellow liquid		
Colour	10	Gardner	ISO 4630
Viscosity @ 25°C	1000 - 2000	mPa.s	ISO 2555
Amine Value	460	mg KOH/g	DIN 16945
Specific Gravity @ 21°C	1.04		ISO 2811
Equivalent	70	Wt/{H}	
Recommended use Level	40	PHR	With bisphenol-A based epoxy resin (EEW=190)

ADVANTAGES

- . Ultra-fast cure and rapid property development at low temperature
- . Excellent surface appearance at low temperature and high humidity conditions
- . Good chemical resistance

APPLICATIONS

- . Marine
- . Protective coating

SHELF LIFE

At least 24 months from the date of manufacture in the original sealed container at ambient temperature. Store away from excessive heat and humidity in tightly closed containers.

HANDLING PRECAUTIONS

Refer to the Safety Data Sheet for Ancamine 2844 curing agent.

TYPICAL CURE SCHEDULE

1 day at ambient temperature.

TYPICAL PERFORMANCE PROPERTIES

Property	Value	Unit	Method
Gel Time	13	mins	Techne Gelation Timer, 150 g mix
Thin Film Set Time @ 23 °C	1/2	h	ASTM D 5895 - Dry hard time
Thin Film Set Time @ 5°C	3/4.5	h	ASTM D 5895 – Dry hard time
Persoz Hardness after 1 / 7 days	200/350	s	ISO 1522
Carbamation Resistance @ 23 °C	5		ISO 2812
Carbamation Resistance @ 5°C	5		ISO 2812

*With bisphenol-A based epoxy resin (EEW=190)

ANCAMINE® is a registered trademark of Evonik Industries AG or one of its subsidiaries.

Disclaimer

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

EVONIK OPERATIONS GMBH

Business Line Crosslinkers
Paul-Baumann-Str. 1
45764 Marl
Germany

www.evonik.com/crosslinkers

Product Information: APCSE@evonik.com

Sample Request: APCSE@evonik.com

EVONIK CORPORATION

Business Line Crosslinkers
7001 Hamilton Boulevard
Trexlerstown, PA 18087
USA

CrosslinkersProinfo@evonik.com

Crosslinkers-Samples@evonik.com

EVONIK SPECIALTY CHEMICALS (SHANGHAI) CO., LTD.

Business Line Crosslinkers
55, Chundong Road
Xinzhuang Industry Park
Shanghai, 201108
China

CL-Asiainfo@evonik.com

CL-Asiainfo@evonik.com

